

Metal	Melting Point
Admiralty Brass	1650 - 1720
Aluminum	1220
Aluminum Alloy	865 - 1240
Aluminum Bronze	1190 - 1215
Antimony	1170
Babbitt	480
Beryllium	2345
Beryllium Copper	1587 - 1750
Bismuth	520.5
Brass, Red	1832
Brass, Yellow	1710
Cadmium	610
Cast Iron, gray	2150 - 2360
Chromium	3380
Cobalt	2723
Copper	1983
Cupronickel	2140 - 2260
Gold, 24K Pure	1945
Hastelloy C	2410 - 2460
Inconel	2540 - 2600
Incoloy	2540 - 2600

Metal	Melting Point
Iridium	4440
Iron, Wrought	2700 - 2900
Iron, Gray Cast	2060 - 2200
Iron, Ductile	2100
Lead	621
Magnesium	1200
Magnesium Alloy	660 - 1200
Manganese	2271
Manganese bronze	1590 - 1630
Mercury	-37.95
Molybdenum	4750
Monel	2370 - 2460
Nickel	2647
Niobium (Columbium)	4473
Osmium	5477
Palladium	2831
Phosphorus	111
Platinum	3220
Plutonium	1180
Potassium	146
Red Brass	1810 - 1880

Metal	Melting Point
Rhenium	5767
Rhodium	3569
Ruthenium	4500
Selenium	423
Silicon	2572
Silver, Coin	1615
Silver, Pure	1761
Silver, Sterling	1640
Sodium	208
Steel, Carbon	2600 - 2800
Steel, Stainless	2750
Tantalum	5400
Thorium	3180
Tin	449.4
Titanium	3040
Tungsten	6150
Uranium	2070
Vanadium	3450
Yellow Brass	1660 - 1710
Zinc	787
Zirconium	3369